















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	60% Split Face (30% Graphite Country, 30% FDL Country), 40% Bedface (Graphite Bedface)
	PATTERN	Natural course 2:1 Random Ashlar
	HEIGHTS	Varies from 2" - 9" (Full Bed); 2"-6" (Thin Veneer)
	LENGTHS	Random, 8"-36" (Full Bed); 8"-24" (Thin Veneer, crated/palletized material can exceed 20")
	DEPTHS	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer)
	COLORS	Black, Charcoal, Gray-Grey
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton (Also Available in Thin Veneer)
	WEIGHT	14.9 lbs per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	Formerly NSVI's "Halifax"; pre-packaged 30% Graphite Country, 30% Fond du Lac Country, 40% Graphite Bedface material.

ASTM C-97

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

ASTM C-170

Parallel to Rift, Dry	36100 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

ASTM C-99

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi



