















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Splitface
	PATTERN	Natural Course Heights 2:1 Random Ashlar
	HEIGHTS	Varies from 2" - 9" (Full Bed & Thin Veneer)
	LENGTHS	Random, 8"-36" (Full Bed); 8"-24" (Thin Veneer, crated/palletized material can exceed 20")
	DEPTHS	3/4" to 1-1/4" (Thin Veneer); 3"-5" (Full Veneer)
	COLORS	Beige, Buff, Gray-Grey, Tan
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	14.9 lbs. per square foot (Thin Veneer)
	FLATS	10 s/f Box, 100 s/f Crate or Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate or Pallet
	NOTES	This was also known as the legacy NSVI product, " Fairmont ". Some photos could show the former NSVI product name.

ASTM C-97

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

ASTM C-170

Parallel to Rift, Dry	36100 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

ASTM C-99

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi



