










## SPECIFICATIONS

	<b>GEOLOGY</b>	Limestone
	<b>TYPE</b>	100% Sawn-Face
	<b>PATTERN</b>	2:1 Coursed, or Dimensional Ashlar   Random Ashlar
	<b>HEIGHTS</b>	2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%): Full Bed & Thin Veneer
	<b>LENGTHS</b>	Random: 8"-20" (Thin Veneer, crated/palletized material can exceed 20"); 8"-48" (Full Bed)
	<b>DEPTHS</b>	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer)
	<b>COLORS</b>	Cream, Gray-Grey, White
	<b>COVERAGE</b>	35-40 Square Feet Per Ton (Full Bed)
	<b>WEIGHT</b>	14 lbs per square foot (Thin Veneer)
	<b>FLATS</b>	10 s/f Box; 100 Sq/ft Crate, 180 Sq/ft Crate; 100 Sq/ft pallet, 180 Sq/ft pallet
	<b>CORNERS</b>	10 Ln/ft Box; 100 Ln/ft Crate; 100 Ln/ft pallet, Crated material can exceed 20"
	<b>NOTES</b>	

### ASTM C-97

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

### ASTM C-170

Parallel to Rift, Dry	36100 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

### ASTM C-99

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

### ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi



**GOLD QUARRY**  
 ANSI/NSC 373-2013  
 C0290908-101



**GOLD FABRICATOR**  
 ANSI/NSC 373-2013  
 C0289215-101