















SPECIFICATIONS

| | | |
|--|-----------------|--|
|  | GEOLOGY | Limestone |
|  | TYPE | 70% Splitface (Graphite Country), 30% Bedface (Graphite Manor) |
|  | PATTERN | Natural Course Heights 2:1 Random Ashlar |
|  | HEIGHTS | Varies from 2" - 9" (Full Bed); 2" - 6" (Thin Veneer) |
|  | LENGTHS | Random, 8" - 36" (Full Bed); 8"-24" (Thin Veneer); Crated/palletized material can exceed 20" |
|  | DEPTHS | 3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer |
|  | COLORS | Beige, Buff, Charcoal, Gray-Grey, Tan |
|  | COVERAGE | Full Bed Depth Veneer: 35-40 Square Feet Per Ton Also Available in Thin Veneer |
|  | WEIGHT | 14.9 lbs. per square foot (Thin Veneer) |
|  | FLATS | 10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet |
|  | CORNERS | 10 l/f Box; 100 l/f Crate; 100 l/f pallet |
|  | NOTES | Aka NSVI's "Zurich"; pre-packaged 70% Splitface (Graphite Country), 30% Bedface (Graphite Manor). |

ASTM C-97

| | |
|-----------------------|----------|
| Water Absorption % | .31 psi |
| Bulk Specific Gravity | 2.83 psi |

ASTM C-170

| | |
|----------------------------|-----------|
| Parallel to Rift, Dry | 36100 psi |
| Parallel to Rift, Wet | 32000 psi |
| Perpendicular to Rift, Dry | 35800 psi |
| Perpendicular to Rift, Wet | 30000 psi |

ASTM C-99

| | |
|-----------------------|----------|
| Parallel to Rift, Dry | 3770 psi |
| Parallel to Rift, Wet | 3500 psi |

ASTM C-880

| | |
|----------------------------|----------|
| Perpendicular to Rift, Dry | 1780 psi |
| Perpendicular to Rift, Wet | 1730 psi |



