















**SPECIFICATIONS**

	<b>GEOLOGY</b>	Sandstone
	<b>TYPE</b>	100% Bedface
	<b>PATTERN</b>	2:1 Natural Coursed Ashlar   or Random Ashlar
	<b>HEIGHTS</b>	2.25 inches, 5 inches, 7.75 inches
	<b>LENGTHS</b>	6 inches - 18 inches
	<b>DEPTHS</b>	3/4 inch - 1.25 inches
	<b>COLORS</b>	Light to medium grays, buff/tan
	<b>COVERAGE</b>	(Not available in full bed-depth)
	<b>WEIGHT</b>	12 lbs per square foot
	<b>FLATS</b>	10 sq ft per Box   100 sq ft Crate   180 sq ft Crate
	<b>CORNERS</b>	10 In ft per Box   100 In ft per Crate
	<b>NOTES</b>	<b>*NEW*</b> Tumbled gray and buff sandstone, with dimensionally sawn heights, packaged assuming a 1/2" mortar joint.

**ASTM C-97**

Water Absorption %	.12 psi
Bulk Specific Gravity	2.78 psi

**ASTM C-170**

Parallel to Rift, Dry	14214 psi
Parallel to Rift, Wet	14213 psi
Perpendicular to Rift, Dry	21814 psi
Perpendicular to Rift, Wet	21320 psi

**ASTM C-99**

Parallel to Rift, Dry	3046 psi
Parallel to Rift, Wet	3191 psi

**ASTM C-880**

Perpendicular to Rift, Dry	4351 psi
Perpendicular to Rift, Wet	4351 psi



**GOLD QUARRIER**  
 ANSI/NSC 373-2013  
 C0290908-101



**GOLD FABRICATOR**  
 ANSI/NSC 373-2013  
 C0289215-101